

ROTOCLEAN

pulitori / scrapers



Poliuretano / polyurethane

	Um	Norme / norms	Valore / value
Peso specifico / specific weight	gr/cm ³		1,26
Durezza a 20°C / hardness at 20 °C	SH/A		88-90
Modulo a 300 % / form to 300%	MPa		17
Modulo a 100 % / form to 100%	MPa		8,7
Modulo a 25 % / form to 25%	MPa		6,5
Modulo a 20 % / form to 20%	MPa		4,7
Modulo a 15 % / form to 15%	MPa		3,4
Modulo a 10 % / form to 10%	MPa		2,4
Modulo a 5 % / form to 5%	MPa		1,4
Test di copressione / compression test 22 H a 70 °C	%		28
Carico di rottura / tensile strength	MPa		45
Allungamento a rottura / elongation at break	%		450
Resistenza alla lacerazione / tear strenght	kN/m		55
Resistenza alla lacerazione / tear strenght (provino C)	kN/m		120
Resa elastica / resilience rebound	%		42
Perdita all'abrasione / abrasion loss	mm ³		50

Anima metallica / metal core

	Um	Norme / norms	Valore / value
Tipo / type			S235JR
Dimensioni / dimensions			40x40x4